

PRODUCT DATA SHEET

SikaCeram®-105

GENERAL PURPOSE, CEMENTITIOUS TILE ADHESIVE.

DESCRIPTION

SikaCeram®105 is a cementitious tile adhesive used for permanent fixing of tiles.
Suitable for tropical and hot climatic conditions.

USES

Suitable for fixing:

- Wall and floor tiles.
- Absorbing / non-absorbed tiles.
- Interior use only.

FEATURES

- Easy to use, just add water.
- Excellent workability.
- Excellent pot life.
- Can be applied directly on cement screeds, concrete or lime mortars.
- Non Toxic.
- Suitable for indoor application.

CERTIFICATES AND TEST REPORTS

SikaCeram®-105 performance is in accordance with European C1T class

PRODUCT INFORMATION

Composition	Cementitious powder, Polymer modified binder.
Packaging	25 kg bag
Shelf life	12 months minimum from production date.
Storage conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between 5 °C and 35 °C. Protect from direct sunlight.
Appearance and colour	Powder
TECHNICAL INFORMATI	ON
Tensile adhesion strength	≥ 0.5 MPa, according to C1T class
APPLICATION INFORMA	ATION
Ambient air temperature	Minimum 5ºC, Maximum 30ºC (Substrate).
Mixing ratio	20-22 % or 5.0 to 5.5 litres clean water per 25 kg bag
Pot Life	Approximately 60 minutes at 30°C.
Open Time	Approximately 20 minutes at 20°C.

PRODUCT DATA SHEET

SikaCeram®-105March 2024, Version 01.04
021710102000000050

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

All technical data stated in this Product Data Sheet are based on laboratory tests.

Actual measured data may vary due to circumstances beyond our control.

Remarks SikaCeram® 105 should not be used directly on gypsum or gypsum board substances. Contact our Technical Service Department for advice.

ECOLOGY, HEALTH AND SAFETY

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Concrete, mortar and masonry surfaces must be clean, free from grease, oil and loosely adhering particles. Suitable mechanical methods such as abrasive blast cleaning; high pressure water jetting at sufficient pressure (minimum 150 bars) and volume; scabbling or needle gunning. On "new" or smooth faced concrete, surfaces as should be Sand-blasted. All surfaces must be as true and flat as possible. Blow holes and irregularities should be filled with suitable SikaTop / Monotop products. Saturate absorbent concrete surfaces thoroughly with water to achieve a surface saturated dry (SSD) condition.

MIXING

Add about 5.0-5.5 litres clean cold water to a clean suitable mixing container. Slowly add the SikaCeram® 105 powder and mix for at least 3 minutes until a homogeneous mix free of lumps is achieved. Do not mix more SikaCeram® 105 than can be used within the open time.

Do not add extra water or other ingredients after mixing!

APPLICATION

Apply SikaCeram® 105 at 3-10 mm thickness directly to the concrete substrate, using a notched trowel and spread the mortar evenly over the area to be tiled. Cover only an area that can be tiled within 15 - 20 minutes. Press tiles firmly into SikaCeram ® 105 with a twisting action to ensure optimum adhesion.

- 1. Use 5.0 5.5 litres of clean water per 25kg bag.
- 2. Mix well with a slow speed drill (maximum 500rpm).
- 3. Apply with "V"-notched trowels for small tiles.
- 4_{IKA} MANUFACTURING REPORTS the trowel for bigger tiles. 5_{10} Research the tiles at the satisfies of the fresh adhesive.

CLEANING OF EQUIPMENT

And Application and mixing tools should be cleaned with web nga sika com water while material is still fresh. Hardened material can only be removed mechanically.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaCeram-105-en-NG-(03-2024)-1-4.pdf

