

PRODUCT DATA SHEET

SikaShield® P23 PE EG 3 mm

APP MODIFIED BITUMEN WATERPROOFING MEMBRANE REINFORCED WITH COMPOUND BASE

DESCRIPTION

SikaShield® P23 PE EG 3 mm Bituminous Waterproofing Membrane made of polymer modified bitumen waterproofing membrane of the highest quality. Sikashield P23 is modified by APP, thus guaranteeing superior performance under various conditions. is reinforced with glass fiber mat & polyester yarn which provides high mechanical and dimensional stability

USES

- Vapor barrier sheet.
- Applications subject to low mechanical stress.
- Waterproofing for wet areas, mechanical rooms, and terraces

FEATURES

- Reinforcement provides the membrane with dimensional stability.
- Improved chemical resistance to acidic and alkaline solutions.
- Environmentally friend.
- Enhanced thermal resistance under a wide range of temperature fluctuation.

PRODUCT INFORMATION

Packaging	Roll size: 1.0 m (roll width) x 10.00 m (roll length).		
Shelf life	24 months from the production date		
Storage conditions	The Product must be stored in original unopened and undamaged packaging in dry conditions and temperatures between +5 °C and +35 °C. Store in a vertical position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.		
Effective thickness	3,0 mm ± 5 %		(EN 1849)
Appearance	<ul style="list-style-type: none"> ▪ Rolled sheet membrane, reinforced. ▪ Surface: smooth ▪ Membrane thickness: 3.00 mm ▪ Colour: Black ▪ Upper surface: covered with Polyolefin film. ▪ Lower surface: laminated with Polyolefin film. 		
Dimensional stability	Longitudinal	± 0.1%	(EN 1107-1)
	Transverse	± 0.1%	
Tear strength	Longitudinal	≥ 350 N	(ASTM D-5147)
	Transverse	≥ 250 N	

Watertightness	Method B: 24 hours at 60 KPa Pass		(EN 1928)
Flow resistance	120 °C		(EN 1110)
Flexibility at low temperature	0 °C		(EN1109)
Maximum tensile force	Longitudinal	450 N / 5 cm - 25%	(EN 12311-1)
	Transverse	300 N / 5 cm - 25%	
Elongation at maximum tensile force	Longitudinal	≥ 5%	(EN 12311-1)
	Transverse	≥ 5%	

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

SUBSTRATE QUALITY

SYSTEM DESIGN

Consider the following when designing the roof system:

- The supporting structure must be of sufficient structural strength to support all new and existing layers of the roof build-up.
- The complete roof system must be designed to withstand and be secured against wind uplift loadings.
- The wind uplift resistance of the adhered roofing assembly is limited by the adhesion strength of the Product to the substrate.

SUBSTRATE CONDITION

The substrate surface must be uniform, firm, smooth and free of any sharp protrusion or burrs, clean, dry, free of grease, laitance, oil, dust and loosely adhering particles.

SUBSTRATE PREPARATION

PRIMING

Primer selection

Note: For information on selecting the appropriate primer, contact Sika technical service.

- Apply the appropriate Sika® primer with the required consumption onto the prepared dry surface.

Note: Refer to the individual Product Data Sheet of the primer.

- Allow the primer to dry before membrane installation.

APPLICATION METHOD / TOOLS

IMPORTANT

Unrolling at low temperatures

At low temperatures, the membrane becomes less flexible.

- Be careful when unrolling to avoid damaging the membrane.

IMPORTANT

Damage through footwear

Footwear with spikes or sharp protrusions may puncture the membrane.

- Use footwear with a flat profile when walking over the membrane.

IMPORTANT

Damage through overheating

- Keep moving the flame while torching to avoid overheating the membrane.

IMPORTANT

Reduced adhesion through insufficient heating

Make sure to heat the membrane sufficiently. If it is not sufficiently heated, the adhesion to the substrate, between layers or on the overlaps will be reduced.

- If the membrane does not adhere to other elements, lift and retorch the unbonded areas.

Seasonal symbol

Note: If a seasonal symbol is printed on the roll's label, it is advisable to use the membrane during the indicated season.

Tackiness at high temperatures

Note: When laying the membrane at high temperatures, the integral adhesive will become 'tacky' and may restrict laying operations.

ALIGNMENT

IMPORTANT

Avoid coinciding joints

To avoid coinciding joints, lay the membranes parallel to one another. When applying on another bituminous membrane, make sure to straddle the overlaps of the previous layer.

- Unroll the membrane.
- Align the membrane.
- Re-roll the membrane before application.

MEMBRANE OVERLAPS

- Overlap the membranes by a minimum of 100 mm on the sides and 150 mm on each end.
- At the end overlap, cut off a corner measuring 100 mm per side at an angle of 45°.
- Weld the overlaps with great care until you see a trickle of melted mixture about 10 mm wide coming

PRODUCT DATA SHEET

SikaShield® P23 PE EG 3 mm
November 2024, Version 01.01
020920011990001976

out along the line of the overlap.

TORCHING

- Heat the substrate and the backing film on the underside of the membrane with a gas burner.
- When the backing film starts to melt, the membrane is ready to stick.
- Roll the heated membrane forward and press it firmly against the substrate to bond it.
- Make sure a bead of melted bitumen is visible along the full length of the overlap sides and ends when laying.

Suitable substrates for torching

- Concrete
- Perlite screed
- Bituminous membranes with a smooth surface
- Coatings (check the compatibility)
- Brick masonry
- Cementitious screeds

DETAILING

- Use a sharp knife to cut in all details such as internal and external corners, upstands, vent pipes, drains, support metalwork etc.

Refer to the relevant method statement for further information on detailing.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA MANUFACTURING NIGERIA LIMITED

10, Western Industrial Avenue, Isheri
Riverview Estate
Lagos - Ibadan Expressway, Ogun State
NIGERIA
Web: nga.sika.com

PRODUCT DATA SHEET

SikaShield® P23 PE EG 3 mm
November 2024, Version 01.01
020920011990001976

SikaShieldP23PEEG3mm-en-NG-(11-2024)-1-1.pdf