

PRODUCT DATA SHEET

Sika® Injection-101 RC

FLEXIBLE PUR-INJECTION FOAM FOR TEMPORARY WATERSTOPPING

DESCRIPTION

Sika® Injection-101 RC is a low viscous, fast foaming and solvent-free water-reactive polyurethane injection foam resin, which cures to a dense flexible foam with a fine cellular structure.

USES

Sika® Injection-101 RC may only be used by experienced professionals.

- Sika® Injection-101 RC is used for the temporary waterstopping of high water intrusions in cracks, joints and cavities in concrete, brickwork and natural stone-work.
- To achieve permanent watertight crack sealing, Sika® Injection-201 CE or Sika® Injection-203 should be injected subsequently.

CHARACTERISTICS / ADVANTAGES

- No reaction takes place unless it is in direct contact with water.
- Sika® Injection-101 RC can be injected as a single component system.
- The free foaming expansion in contact with water is up to 40 times.
- The reaction speed (foam formation) is influenced by the temperatures of the mixed material, the structure and the contact water, plus the hydrodynamic conditions.
- In cold temperatures (< + 10°C) Sika® Injection-101 RC can be accelerated using Sika® Injection-AC10.

APPROVALS / CERTIFICATES

German KTW drinking water certificate
German ZTV-ING chapter 3, part 5 (RISS) tested (BAST listed)

PRODUCT INFORMATION

Composition	Water reactive 2-part polyurethane resin, solvent and CFC free		
Packaging	Part A	10 or 20 kg	
	Part B	12.5 or 25 kg	
Colour	Part A	Colourless	
	Part B	Brown	
Shelf life	24 months shelf life from date of production if stored properly in undamaged, unopened, original sealed packaging.		
Storage conditions	Dry storage at temperatures from +5 °C up to +35 °C. Protect from direct sunlight and humidity.		
Density	Part A	~1.0 kg/l	(ISO 2811)
	Part B	~1.25 kg/l	
	at 20 °C		

Viscosity	Part A	~140 mPa·s	(ISO 3219)
	Part B	~155 mPa·s	
at 20 °C			

TECHNICAL INFORMATION

Expansion	Expansion start	~15 s after contact with water	(EN 1406)
	Expansion end	~67 s	
at 20 °C			

APPLICATION INFORMATION

Mixing Ratio

part A:part B = 1:1 by volume
Reaction time table Sika® Injection-101 RC
 [PM 10081-11]

0 % Sika® Injection-AC10¹		
Material temperature	Expansion start	Expansion end
+5 °C	~19 sec	~79 sec
+10 °C	~17 sec	~88 sec
+20 °C	~16 sec	~70 sec
5 % Sika® Injection-AC10¹		
Material temperature	Expansion start	Expansion end
+5 °C	~12 s	~57 s
+10 °C	~11 s	~49 s
+20 °C	~10 s	~39 s
10 % Sika® Injection-AC10¹		
Material temperature	Expansion start	Expansion end
+5 °C	~9 s	~41 s
+10 °C	~8 s	~37 s
+20 °C	~7 s	~35 s

¹ Dosage of Sika® Injection-AC10 in % by weight of Sika® Injection-101 RC (comp. A+B)
 The given data are laboratory parameters and may deviate depending on the object and conditions on site.

Ambient Air Temperature	+5 °C min. / +35 °C max.	
Substrate Temperature	+5 °C min. / +35 °C max.	
Pot Life	~2 hours (at + 20 °C) remove skin from the surface (do not mix in!)	(ISO 9514)

APPLICATION INSTRUCTIONS

MIXING

Empty parts A and B into a mixing vessel and mix slowly and thoroughly for at least 3 min (max. 250 rpm) until homogeneous, thereby observing the safety precautions. The containers are supplied according to the required mixing ratio of 1 : 1 parts by volume. Partial quantities can be measured out in separate vessels. After mixing, pour the material into the pump's feed container, stir briefly and apply within the pot life. After mixing, pour the material into pump's feed container, stir briefly and use within the pot life. If the substrate and/or ambient temperatures are < +10 °C, Sika® Injection-AC10 can be added to Sika® Injection-101 RC to accelerate the start of expansion.

APPLICATION METHOD / TOOLS

Use injection pumps suitable for single part injection products.

CLEANING OF EQUIPMENT

Clean all tools and application equipment according to the Product Data Sheet for the Sika® Injection Cleaning System.

IMPORTANT CONSIDERATIONS

Sika® Injection-101 RC is generally used for the temporary stopping of high water infiltration. To achieve permanent watertight crack sealing, the subsequent injection of Sika® Injection-201 CE or Sika® Injection-203 is recommended.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Manufacturing Nigeria LTD

10, Western Industrial Avenue,
Isheri Riverview Estate,
Lagos-Ibadan Expressway,
Nigeria.
Tel.: +234 80 90 44 22 21
nga.sika.com



PRODUCT DATA SHEET
Sika® Injection-101 RC
May 2020, Version 01.0
020707010010000001

