

## PRODUCT DATA SHEET

# SikaPlast® GL 118

(formerly MasterGlenium® 118)

Polycarboxylic ether-based superplasticizer to produce high-quality ready-mix concrete

### DESCRIPTION

**SikaPlast® GL 118** is an innovative latest generation superplasticizer based on polycarboxylic ether (PCE) polymers and is specially engineered for ready-mix concrete.

**SikaPlast® GL 118** greatly improves cement dispersion. At the start of the mixing process the same electrostatic dispersion occurs but the presence of the lateral chains, linked to the polymer backbone, generate a steric hindrance which stabilises the cement particles capacity to separate and disperse. This mechanism provides flowable concrete with greatly reduced water demand.

### USES

SikaPlast® GL 118 is used to produce high-quality ready-mix concrete.

### FEATURES

- Capability of delivering high performance concrete.
- Production of a concrete with low water cement ratios with excellent workability retention properties.
- A versatile product for many application requirements.
- Easier placing and faster strength development.
- Improved concrete surfaces.
- Insurance that concrete meets original specification.
- High quality durable concrete.

### PRODUCT INFORMATION

<b>Packaging</b>	SikaPlast® GL 118 is available in 1000 litre IBCs or in bulk.
<b>Appearance and colour</b>	Brown liquid
<b>Shelf life</b>	The shelf life is 12 months from date of manufacture when stored correctly.
<b>Storage conditions</b>	SikaPlast® GL 118 should be stored out of direct sunlight and protected from extremes of temperatures. The occurrence of a surface layer with SikaPlast® GL 118 is normal and will have no effect on the performance of the product.
<b>Density</b>	1.05 ± 0,02
<b>pH-Value</b>	5 ± 1,5
<b>Conventional dry material content</b>	19 ± 2 (%)
<b>Total chloride ion content</b>	“Chloride-free” to EN 934-2

# APPLICATION INFORMATION

<b>Recommended dosage</b>	The normally recommended dosage rate of SikaPlast® GL 118 is: <b>0.4 to 1.5 litres per 100kg</b> of total cementitious material. Other dosages may be recommended in special cases according to specific site conditions. In this case, please consult our Technical Services Department for advice. It is recommended that trials be conducted with the actual materials to be used and at the specified SikaPlast® GL 118 dose rates to verify performance before proceeding to application.
<b>Compatibility</b>	SikaPlast® GL 118 is suitable for mixes containing: <ul style="list-style-type: none"><li>▪ Microsilica (Silica Fume)</li><li>▪ Fly Ash (PFA)</li><li>▪ GGBS (ground granulated blast furnace slag)</li></ul>
<b>Dispensing</b>	SikaPlast® GL 118 is a ready-to-use admixture to be added to the concrete as a separate component. Optimal results are obtained if SikaPlast® GL 118 is poured into the concrete mix right after the addition of the first 80% of the mixing water, i.e. when all solids are wetted. Avoid adding the admixture to the dry aggregates.

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER DOCUMENTATION

SikaPlast® GL 118 contains no hazardous substances requiring labelling. For further information refer to the Material Safety Data Sheet.

## ECOLOGY, HEALTH AND SAFETY

### LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**SIKA MANUFACTURING NIGERIA LIMITED**  
10, Western Industrial Avenue, Isheri  
Riverview Estate  
Lagos - Ibadan Expressway, Ogun State  
NIGERIA  
Web: nga.sika.com

**PRODUCT DATA SHEET**  
SikaPlast® GL 118  
January 2025, Version 04.01  
02130100000002362

SikaPlastGL118-en-NG-(01-2025)-4-1.pdf

