

**BUILDING TRUST** 

# PRODUCT DATA SHEET Sika AnchorFix®-3030

Epoxy, high-performance, chemical anchoring adhesive

### DESCRIPTION

Sika AnchorFix<sup>®</sup>-3030 is a two-part, thixotropic, highperformance epoxy anchoring adhesive. It is used for anchoring threaded rods and reinforcing bars in both cracked and uncracked, dry and damp concrete.

#### USES

Sika AnchorFix<sup>®</sup>-3030 may only be used by experienced professionals.

Sika AnchorFix<sup>®</sup>-3030 is used as an anchoring adhesive for fixing non-expanding anchors in the following substrates:

- Concrete
- Cracked or uncracked concrete
- Wood
- Natural stone
- Reconstituted or cast stone
- Solid rock

Sika AnchorFix<sup>®</sup>-3030 is used as an anchoring adhesive for fixing non-expanding anchors in the following obiects:

- Threaded rods
- Reinforcing steel
- Bolts and special fastening systems

Sika AnchorFix<sup>®</sup>-3030 is used for the following application areas:

- Around window and door frames
- Handrails, balustrades and supports
- Railings
- Please note:
- The Product may only be used by experienced professionals.

# FEATURES

- Suitable for use in dry, wet, and water-filled holes
- ETA based on working life of 50 years or 100 years
- Long open time
- Very good load capacity

PRODUCT DATA SHEET Sika AnchorFix®-3030 February 2025, Version 03.01 020205010030000007

- ETA to EAD 330499-01-0601 for anchoring in uncracked concrete
- ETA to EAD 330087-01-0601 for post installed rebar connections
- ETA to TR 069 for bond splitting
- Seismic testing C1 and C2 available
- Suitable for contact with drinking water
- High fire resistance
- Styrene-free
- Good adhesion to the substrate
- No shrinkage after curing
- Low wastage
- Seismic testing for post installed rebars
- Fire exposure testing F240 for rebars
- Can be used in hammer, dustless and diamond drilled bore holes

### SUSTAINABILITY

 Contributes towards satisfying Indoor Environmental Quality (EQ) Credit: Low-Emitting Materials under LEED<sup>®</sup> v4 — 1–3 points

# **CERTIFICATES AND TEST REPORTS**

- CE marking and declaration of performance based on European Technical Assessment ETA 17/0693 06/05/2024. ETA issued on the basis of EAD 330087-01-0601 Post-installed rebar connections.
- CE marking and declaration of performance based on European Technical Assessment ETA-17/0694. ETA issued on the basis of EAD 330499-01-0601 Bonded fasteners for use in concrete.
- European Technical Assessment ETA 17/0693 06/05/2024
- European Technical Assessment ETA 17/0694 25/10/2021
- European Technical Assessment ETA 24/0384 06/05/2024
- Fire Evaluation of Post Installed Rebar Connections CEN EN 1991-1-2, Sika Anchor
- Drinking Water System Components NSF/ANSI 61, Sika AnchorFix<sup>®</sup>, IAPMO R&T, Certificate No. K-8319

# **PRODUCT INFORMATION**

	Epoxy resin				
Packaging	385 ml dual cartrid	lge	12 cartridges p 70 boxes per p		
	585 ml dual cartrid	585 ml dual cartridge 12 cartridge per p			
	56 boxes per pa			allet	
	Refer to the current price list for available packaging variations.				
Colour	Part A	Part A off white			
	Part B	Part B		grey	
	Part A+B				
Shelf life	18 months from da	ate of pro	duction		
Storage conditions	packaging in dry co Protect the Produc	onditions a ct from dir	in original, unopened an at temperatures betweer rect sunlight. Data Sheet for informatio	n +5 °C and +25 °C.	
Density	1.5 kg/L (parts A+B	s mixed)			
				(ISO 1183-1)	
TECHNICAL INFORMATION	I			(ISO 1183-1	
Compressive strength	Cured 7 days at +2	0°C	95 N/mm²	(ISO 1183-1) (ASTM D695)	
	-		95 N/mm <sup>2</sup> 45 N/mm <sup>2</sup>		
Compressive strength	Cured 7 days at +2	0 °C		(ASTM D695)	
Compressive strength Flexural-strength	Cured 7 days at +2	0 °C	45 N/mm <sup>2</sup>	(ASTM D695)	
Compressive strength Flexural-strength Tensile strength	Cured 7 days at +20 Cured 7 days at +20 Cured 7 days at +20	0 °C	45 N/mm <sup>2</sup> 23 N/mm <sup>2</sup> 5500 N/mm <sup>2</sup>	(ASTM D695) (ASTM D790) (ASTM D638)	
Compressive strength Flexural-strength Tensile strength Modulus of elasticity in tension	Cured 7 days at +20 Cured 7 days at +20 Cured 7 days at +20 Cured 7 days at +20 Cured 7 days at +20	0 °C 0 °C 0 °C	45 N/mm <sup>2</sup> 23 N/mm <sup>2</sup> 5500 N/mm <sup>2</sup>	(ASTM D695) (ASTM D790) (ASTM D638) (ASTM D638)	

#### **APPLICATION INFORMATION**

Mixing ratio	Part A : Part B	3 : 1 by volume	
Layer thickness	Maximum	8 mm	
Sag flow	Non-sag, even overhead		
Material temperature	Maximum	+40 °C	
	Minimum	+10 °C	
Ambient air temperature	Maximum	+40 °C	
	Minimum	+5 °C	
Dew point	The substrate temperature must be at least +3 °C above dew point to re- duce the risk of condensation decreasing adhesion.		
Substrate temperature	Maximum	+40 °C	
	Minimum	+5 °C	

PRODUCT DATA SHEET Sika AnchorFix®-3030 February 2025, Version 03.01 020205010030000007



**BUILDING TRUST** 

Curing	time
--------	------

ing time	Temperature	Open time - T <sub>gel</sub>	Curing time - T <sub>cur</sub>
	+35 °C to +40 °C	6 minutes	2 hours
	+30 °C to +35 °C	8 minutes	4 hours
	+25 °C to +30 °C	12 minutes	6 hours
	+20 °C to +25 °C	18 minutes	8 hours
	+15 °C to +20 °C	25 minutes	12 hours
	Minimum cartridge		
	temperature: +15 °C		
	+10 °C to +15 °C	40 minutes	18 hours
	+5 °C to +10 °C	150 minutes	24 hours
	Minimum cartridge		
	temperature: +10 °C		
	<+5 °C	300 minutes	24 hours
	Minimum cartridge		
	temperature: +10 °C		

#### SYSTEM INFORMATION

#### System structure

Ancillary products:

- Sika AnchorFix<sup>®</sup> Flexible Extensions
- Sika AnchorFix<sup>®</sup> Hole Cleaning Brushes Steel
- Sika AnchorFix<sup>®</sup> Static Mixers / Nozzles
- Sika AnchorFix<sup>®</sup> Straight Extensions
- Sika AnchorFix<sup>®</sup> Resin Stoppers

# **BASIS OF PRODUCT DATA**

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

### FURTHER DOCUMENTATION

For design details, refer to the following technical documentation: 870 43 18 Technical Documentation Sika AnchorFix®-3030 (08 / 2023) 1

### **IMPORTANT CONSIDERATIONS**

 Natural / reconstituted stone and solid rock properties vary particular with regard to strength, composition and porosity. For each application, the suitability of Sika AnchorFix®-3030 must be tested for bond strength, surface staining and discoloration by first applying the product to a sample area before full project application.

# ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

### APPLICATION INSTRUCTIONS

#### SUBSTRATE QUALITY

Mortar and concrete must be at the required design strength.

PRODUCT DATA SHEET Sika AnchorFix®-3030 February 2025, Version 03.01 020205010030000007

Substrate tensile / compressive strengths (concrete, masonry, natural stone) must be confirmed by testing. The anchor hole must always be clean, dry, free from oil and grease etc.

Loose particles must be removed from the holes. Threaded rods and rebar's must be cleaned thoroughly and free from dirt, oil, grease, corrosion products or any other substances and particles which could affect adhesion.

#### SUBSTRATE PREPARATION

Mortar and concrete must be older than 28 days. Verify the substrate strength (concrete, masonry, natural stone). Perform pull-out tests if the substrate strength is unknown.

Make sure that the anchor hole is clean, dry, free from oil and grease. Remove loose particles from the anchor hole.

Clean threaded rods and reinforcement bars thoroughly. Remove oil, grease or any other substances and particles such as dirt.

#### MIXING

PREPARING THE CARTRIDGE


- 1. Unscrew the cap.
- 2. Remove the cap.
- 3. Screw on the static mixer.
- 4. Place the cartridge into the dispenser and start application.


#### **APPLICATION METHOD / TOOLS**

#### Anchors in solid masonry/concrete

**BUILDING TRUST** 








1. Drill hole with an electric drill to the diameter and depth required. Drill hole diameter must be in accordance with anchor size

2. The drill hole must be cleaned with oil free compressed air using an air lance, pressure: 6 Bar (90 psi). Start from the bottom of the hole and clean minimum 2 x until return air stream is free of dust





3. The drill hole must be thoroughly cleaned with the special steel brush (brush at least 2x). The diameter of the brush must be larger than the diameter of the drill hole


4. The drill hole must be cleaned again as stage 2





5. The drill hole must be thoroughly cleaned again as stage 3











or loaded

10. During the resin

hardening time the anchor must not be moved

Important Note: Anchors in hollow blocks: Use Sika AnchorFix<sup>®</sup>-1.

6. The drill hole must be cleaned again as stage 2 & 4

7. Pump gun at least 2 x until both parts are extruded as a one consistant colour. Do not use this material. Release the gun pressure and clean the static mixer opening with a cloth

8. Inject the adhesive into the drill hole, starting from the bottom and slowly pull out the static mixer while extruding the resin into the hole. Avoid entrapping air. For deep holes use extension tubing

9. Insert the anchor with a rotary motion into the filled drill hole within the adhesive open time. Some of the adhesive must flow out of the hole

 PRODUCT DATA SHEET

 Sika AnchorFix®-3030

 February 2025, Version 03.01

 020205010030000007



#### APPLICATION

When the work is interrupted, the static mixer nozzle can remain on the cartridge after the gun pressure has been released. If the resin has hardened in the nozzle when work is resumed, a new nozzle must be attached.

Test if the Product is suitable for the substrate

Note: Due to the variety of possible substrates, the Product's suitability for the substrate must be confirmed before application, particularly in terms of desired bond strength, composition, porosity, potential surface staining or discolouration.

1. Test the Product's suitability in a sample area. ANCHORS IN SOLID MASONRY OR CONCRETE

- 1. IMPORTANT Make sure that the drill hole diameter is in accordance with the anchor size. Drill a hole with an electric drill to the diameter and depth specified in the Technical Documentation listed in the section Further Information.
- 2. IMPORTANT Use oil-free compressors. Clean the drill hole with an air lance, pressure: 6 Bar (90 psi), starting from the bottom of the hole. Note The hole must be cleaned a minimum of two times until return air stream is free of dust.
- 3. Thoroughly clean the drill hole with the steel brush. Note The diameter of the brush must be larger than the diameter of the drill hole and the hole must be cleaned a minimum of two times.
- 4. IMPORTANT Use oil-free compressors. Clean the drill hole with an air lance, pressure: 6 Bar (90 psi), starting from the bottom of the hole. Note The hole must be cleaned a minimum of two times until return air stream is free of dust.
- 5. Thoroughly clean the drill hole with the steel brush. Note The diameter of the brush must be larger than the diameter of the drill hole and the hole must be cleaned a minimum of two times.
- 6. IMPORTANT Use oil-free compressors. Clean the drill hole with an air lance, pressure: 6 Bar (90 psi), starting from the bottom of the hole. Note The hole must be cleaned a minimum of two times until return air stream is free of dust.
- 7. Pump the Product until both parts come out uniformly. Release the gun pressure and clean the cartridge nozzle with a cloth.
- 8. IMPORTANT Do not entrap air into the hole. Inject the Product into the hole starting from the bottom while slowly drawing back the static mixer. Note For deep holes extension tubing can be used.
- IMPORTANT The anchor must be placed within the open time. Insert the anchor with a rotary motion into the filled drill hole. Note Some adhesive must come out of the hole.
- 10. Do not load or move the anchor during the hardening time.

#### SIKA MANUFACTURING NIGERIA LIMITED

10,Western Industrial Avenue, Isheri Riverview Estate Lagos - Ibadan Expressway, Ogun State NIGERIA Web: nga.sika.com

#### sure has Colma Cle

Clean all tools and application equipment with Sika<sup>®</sup> Colma Cleaner immediately after use. Hardened material can only be removed mechanically.

### LOCAL RESTRICTIONS

CLEANING OF EQUIPMENT

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

# **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaAnchorFix-3030-en-NG-(02-2025)-3-1.pdf



PRODUCT DATA SHEET Sika AnchorFix®-3030 February 2025, Version 03.01 020205010030000007

**BUILDING TRUST**