

PRODUCT DATA SHEET

Sikadur® ADH 1414

(formerly MBrace ADH 1414)

Wet-to-dry and vertical dowel Epoxy bonding agent for concrete repairs, bonding concrete to concrete, steel and granolithic toppings

DESCRIPTION

Sikadur® ADH 1414 is a permanent epoxy adhesive for internal or external bonding of renderings, granolithic toppings, and concrete to concrete. It tolerates a degree of moisture before and during curing and is insoluble when cured. The ultimate bond strength is greater than the tensile strength of concrete. Sikadur® ADH 1414 does not shrink and provides an even and stress-free bond

tests.

USES

Sikadur® ADH 1414 may be applied to clean, sound and durable surfaces, i.e. steel, glazed tiles and bricks, ceramic and quarry tiles, terrazzo tiles and floors. Also, to smooth and worn granolithic paving, old and worn concrete, engineering, and semi-engineering bricks.

FEATURES

- High strength
- Non shrink
- Moisture tolerant
- Durable
- Resistant to chemical attack
- Supplied in pre-weighed units

CERTIFICATES AND TEST REPORTS

ASTM C881 Type 2 Grade 2, Class B & C.
All products originating from MB Construction Chemicals Solutions South Africa (Pty) Ltd are manufactured under a management system independently certified to conform to the requirements of the quality standards ISO 9001, environmental and occupational health and safety standards.

* Properties listed are based on laboratory controlled

PRODUCT DATA SHEET

Sikadur® ADH 1414

September 2024, Version 02.02

020204000000002022

PRODUCT INFORMATION

Packaging	Sikadur® ADH 1414 is available in 2 litre kits containing the base resin and reactor component. (Base = 1.76kg ; Reactor = 1.56kg, Total = 3.32kg).
Shelf life	
Storage conditions	Store under cover out of direct sunlight and protect from extremes of temperature. In tropical climates the product must be stored in an air-conditioned environment. Shelf life is 12 months from date of manufacture when stored in undamaged, unopened packaging. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging. For specific storage and disposal advice consult Master Builders Solutions' Technical Services Department.
Density	Mixed density @25°C = 1485kg/m ³
Consumption	1 Litre (1.66kg) = 1m ² per 1mm thickness dependent on substrate profile.
Pot Life	25°C - 2 hours 40°C – 3/4 hours
Tack free time	≥45 N/mm ² 7 days

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS OF USE

TEMPERATURE

Since low temperatures retard the setting and curing of Sikadur® ADH 1414, avoid working in cold weather if possible. Although Sikadur® ADH 1414 will cure slowly at low temperatures, a temperature of 7°C to 10°C can be considered to be the lowest at which work on vertical rendering may proceed satisfactorily without shuttering.

FURTHER DOCUMENTATION

Technical support, where provided, does not constitute supervisory responsibility. For additional information contact your local MB Construction Chemicals Solutions South Africa (Pty) Ltd representative. MB Construction Chemicals Solutions South Africa (Pty) Ltd shall not be liable for technical advice provided. MB Construction Chemicals Solutions South Africa (Pty) Ltd reserves the right to have the true cause of any difficulty determined by accepted test methods. Undertaking such tests is not, and shall not be deemed to be, an admission of liability or an assumption of any risk, loss, damage or liability.

ECOLOGY, HEALTH AND SAFETY

As with all chemical products, care should be taken during use and storage to avoid contact with eyes, mouth, skin and foodstuffs (which can also be tainted with vapour until product fully cured or dried). Treat

splashes to eyes and skin immediately. If accidentally ingested, seek immediate medical attention. For further information refer to the material safety data sheet.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

All surfaces must be thoroughly cleaned and prepared. All loose particles, laitance, dust, curing compounds, floor hardeners, oil, grease, fat, bitumen and paint must be removed if good bond strength is to be achieved. Gloss surfaces must be abraded.

If oil, grease, fat, etc. are present, they should be removed before starting any other form of preparation. All laitance weak or friable concrete should be removed by chipping, grit blasting, or scabbling until a sound base is obtained.

All laitance should be removed by mechanical scarification, grit blasting, or by acid etching. Visible signs of mould growth, lichen, or algae should be removed and treated with a fungicidal wash.

New concrete should have cured until the shrinkage and moisture movement is low. Surfaces heavily impregnated with mould oil should be degreased and grit blasted or mechanically scarified to remove the contaminated surface. All curing compounds should have disintegrated or be removed, and application carried out only onto a clean, dust free surface.

MIXING

Carefully transfer the entire contents of the smaller container of Sikadur® ADH 1414 REACTOR COMPONENT to the larger Sikadur® ADH 1414 COMPONENT tin and thoroughly mix, using a stout palette knife or a slow running drill with a paint mixing paddle until uniformity is achieved. This normally takes about three

PRODUCT DATA SHEET

Sikadur® ADH 1414

September 2024, Version 02.02

02020400000002022

minutes. Do not attempt to mix only part of the contents. Do not attempt to thin Sikadur® ADH 1414.

APPLICATION

Sikadur® ADH 1414 should be applied evenly across the whole surface with a clean, short haired paint brush or a laying-on trowel. After application, the Sikadur® ADH 1414 must be left to stand before overcoating. The time delay will depend on surface and prevailing conditions but will typically be 60 minutes at 25°C or 45 minutes at 40°C. The Sikadur® ADH 1414 should be protected during this time to prevent contamination. This is particularly necessary on horizontal surfaces.

RENDERINGS AND SCREEDS

Once the render or screed has been applied over the Sikadur® ADH 1414 recognised methods of working may be adopted.

It is essential that granolithic paving and sand cement renders and screeds are cured. This can be achieved by curing with a fine spray of clean water and polythene sheeting. More effective is to spray the surface with a curing membrane from the MasterKure range. Failure to observe these precautions may cause the render or screed to crack.

Expansion joints formed in the substrate should be carried through the rendering or screed and may be filled with Sikaflex® GG 470, 2 part polysulphide joint sealant.

CLEANING OF EQUIPMENT

Use Methyl Ethyl Ketone to clean tools when Sikadur® ADH 1414 is still wet or tacky. Once Sikadur® ADH 1414 has set hard, it can only be removed by chipping or burning.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika re-

SIKA MANUFACTURING NIGERIA LIMITED

10, Western Industrial Avenue, Isheri
Riverview Estate
Lagos - Ibadan Expressway, Ogun State
NIGERIA
Web: nga.sika.com

PRODUCT DATA SHEET

Sikadur® ADH 1414
September 2024, Version 02.02
02020400000002022

serves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikadurADH1414-en-NG-(09-2024)-2-2.pdf