

# PRODUCT DATA SHEET

## Sikafloor®-958 PG

A polymeric water and stain resistant burnishing finish designed to protect polished concrete surfaces

### DESCRIPTION

Sikafloor® - 958 PG is a polymeric water and stain resistant burnishing finish that is designed to guard and protect smooth ground and polished concrete surfaces.

Its organo-silicate hybrid composition combines the densifying and abrasion resistant properties of lithium silicate, with the stain blocking properties found only in self-crosslinking organic systems.

Applied after application of a quality concrete densifier, Sikafloor® - 58 PG should be polished to the desired gloss level with high-speed floor burnishing equipment. Properly installed, a thin yet durable film with good moisture transmission properties remains. This film will not crack, peel, or delaminate under normal conditions.

### USES

Use as a final concrete polish to guard and protect interior:

- Smooth ground concrete floors
- Ground flat exposed aggregate
- Ground smooth embedded terrazzo
- Ground smooth cementitious overlays
- Countertops

### FEATURES

- Adds water and stain resistance.
- Low odor, non-yellowing water based formulation.
- Breathable thin film forming surface treatment.
- Bonds directly to cement and aggregate silicates.
- Effectively locks in concrete dyes.
- Shortens concrete polishing times.
- Does not gum burnishing equipment.
- UV light stable.
- Cures to a non-toxic surface.
- Apply by spray and mop.

### CERTIFICATES AND TEST REPORTS

Sikafloor® -958 PG can be used as part of a low VOC concrete polishing system to earn LEED® credits for Indoor Environmental Quality, EQ Credit 4.2: Low-Emitting Materials: Paints & Coatings.

Sikafloor® - 958 PG can be used to make floors that exceed the Underwriters Laboratories Safety Standard UL 410, "Slip Resistance of Floor Surface Materials."



### PRODUCT INFORMATION

<b>Composition</b>	Lithium Silicate with proprietary polymeric polish and water repellent.
<b>Packaging</b>	1-gallon (3.8 L) cans, 5-gallon (18.9 L) pails, and 55-gallon (208 L) drums.
<b>Appearance and colour</b>	Milk like liquid. When installed, it is colorless clear.

<b>Shelf life</b>	18 months from the date of manufacture. 1 month after opening.
<b>Storage conditions</b>	Store in original containers at 40°F to 110°F (4°C - 43°C). DO NOT FREEZE!

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER DOCUMENTATION

Sikafloor®- 958 DC is marketed internationally through strategically located representatives. Sika offers a complete line of engineered systems for coloring, texturing, and improving performance in architectural concrete. Sikafloor Systems address specialized requirements for interior, exterior and vertical uses with compatible systems of complementary products.

## IMPORTANT CONSIDERATIONS

Sikafloor® - 958 PG is not a curing compound. It is intended only for use on ground and polished concrete. It is a penetrating and reactive material that functions without forming any appreciable film or coating. It is not intended for use on underwater applications. Water and stain repellency of treated substrates will develop over time; 2 weeks is generally sufficient. Surfaces treated with Sikafloor®-958 PG should not be cleaned with or exposed to acidic cleaners or substances.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

If using spray equipment, always wear protective respirator. Mask adjacent areas to protect property from splashes and overspray. Dried material will be difficult to remove. Remove overspray immediately with soap and water.

### Product Dilution

First applications of Sikafloor®-958 PG should be made full strength without dilution. Second passes or maintenance applications can be diluted 1:1 with water.

### Coverage

Coverage will depend upon method of application, surface porosity, age, moisture, absorption characteristics and the texture of the concrete. The application of two thin coats prior to burnishing is recommended. Spread rate on flat finished concrete that has been ground, densified, and roughly polished with a 400 grit abrasive disk, is typically 1200-1500 ft<sup>2</sup>/gal (36.7 - 49.0 m<sup>2</sup>/L). Slabs ground to expose hard non absorptive aggregates will take less material. For all uses and applica-

tions, spread or scrub puddles of excess material into surfaces before it is allowed to dry. Puddled material allowed to dry can form unsightly salts that are difficult to polish.

## EQUIPMENT

Apply by low pressure pump-spray application, followed by thorough spreading and distribution with a microfiber mop or floor wax applicator to work material into substrate pores.

High-speed burnishing equipment will be required along with coarse through super fine diamond impregnated polishing disks. Disks beginning with 400 grit, and progressively finer will be needed. Typical sequences of disks used include 400, 800, 1200, and 3000 grit. Final grit selection will determine final gloss. Always wear protective clothing and personal protection equipment proper for the method of application and burnishing.

## SUBSTRATE QUALITY / PRE-TREATMENT

For best results, all concrete should be fully cured and at least 28 days old so that the slab has reached full hardness. Surfaces must be clean of all prior sealers, curing compounds, oils, or other foreign materials that might prevent penetration.

Surfaces should already be densified. If dyes have been used, they should be locked in with a densifier and ground and polished with at least a high-speed 400 grit diamond impregnated polishing pad prior to application of Sikafloor® -958 PG.

**Mixing:** Mix until uniform before using.

#### **Jobsite Test Sections**

Verify and approve suitability and appearance by making jobsite test sections prior to general application. Each individual concrete color, finishing technique, densifier, sealer, and polish combination should be verified. Test sections must be of adequate size to be representative and be produced by the same workers who will apply product to the larger job. Test completed systems for wet and dry slip resistance to ensure they are safe. Do not proceed with products, techniques, or finishing systems that do not meet required safety specifications or site owner approval.

#### **APPLICATION**

Mask all areas not to be coated to safeguard against splashes, overspray, and runoff from application. Wear all required safety equipment. Take care not to allow tape adhesive to interfere with surfaces to be treated. Surfaces wet with material will be slippery until dry.

Distribute product with a pump garden sprayer to fully saturate the surface. Spread material with flat microfiber pad or floor wax applicator. Allow the material to dry to touch, and apply a second coat. Take care not to create lap marks as they are difficult to remove once the product has dried. If too much material has been applied, and it is puddled after 30 minutes, dilution and removal with a wet vacuum is recommended. When the second application is dry, high-speed burnishing and polishing with progressively finer grit abrasive pads can begin.

**Dry times** will depend upon weather conditions. At 70°F (21°C) and 50% relative humidity surfaces should be dry and able to be polished in 1 hour. Sikafloor® -58 PG has a self-crosslinking component, best results will be achieved if the final high-gloss polishing is performed after an overnight dry.

#### **CLEANING OF EQUIPMENT**

Clean equipment with warm water and detergent immediately after application.

#### **LOCAL RESTRICTIONS**

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

#### **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**SIKA MANUFACTURING NIGERIA LIMITED**  
10,Western Industrial Avenue, Isheri  
Riverview Estate  
Lagos - Ibadan Expressway, Ogun State  
NIGERIA  
Web: [nga.sika.com](http://nga.sika.com)

#### **PRODUCT DATA SHEET**

Sikafloor®-958 PG

January 2026, Version 01.01

020815110010000021

Sikafloor-958PG-en-NG-(01-2026)-1-1.pdf

**BUILDING TRUST**

