

## PRODUCT DATA SHEET

# Sikament® RB 846

(formerly MasterRheobuild® 846)

High range, water-reducing superplasticizer for rheoplastic concretes

### DESCRIPTION

Sikament® RB 846 is formulated from synthetic polymers specially designed to impart rheoplastic qualities to concrete.

A rheoplastic concrete is a fluid concrete with a slump of at least 200mm, easily flowing, but at the same time free from segregation and having the same w/c ratio as that of a low slump concrete (25mm) without admixture.

Sikament® RB 846 is chloride-free.

### USES

- Microsilica concrete
- Mass concrete pours
- Ready-mixed concrete
- Long-distance transport
- Pumped concrete
- Casting in hot climates

### PRODUCT INFORMATION

<b>Packaging</b>	1000 lt. flow bins. Bulk supply in tanker trucks is available upon request
<b>Shelf life</b>	Up to 12 months if stored according to manufacturer's instructions in unopened containers.
<b>Storage conditions</b>	Sikament® RB 846 must be stored where temperatures do not drop below +5°C. If product has frozen, thaw and agitate until completely reconstituted. Store under cover, out of direct sunlight and protect from extremes of temperature.
<b>Colour</b>	Dark brown liquid
<b>Density</b>	(1.180 - 1.210) at 25° C
<b>Total chloride ion content</b>	Nil to BS 5075

### FEATURES

- Reduced thermal peaks
- High workability for longer periods
- Lower pumping pressure
- Delayed setting with longer workability
- Higher ultimate strengths
- Reduced permeability
- Improved durability

### CERTIFICATES AND TEST REPORTS

Complies with ASTM C-494 Type B, D and G

## APPLICATION INFORMATION

---

### Recommended dosage

Optimum dosage of Sikament® RB 846 should be determined in trial mixes. As a guide, the following dosages are recommended as a starting point for any trial: in normal concrete, a dosage of between 0.8% and 2%; in high performance microsilica concrete, a dosage of between 1.5 and 3%. Dependent upon mix requirement, it is possible to use a higher dosage of Sikament® RB 846 without causing any adverse effects upon the concrete.

---

### Dispensing

Sikament® RB 846 is a ready-to-use liquid, which is dispensed into the concrete together with mixing water. The plasticising effect, or water reduction, is higher if the admixture is added to the concrete after 50-70% of the mixing water has been added. The addition of Sikament® RB 846 to dry aggregate or cement is not recommended. Automatic dispensers are available.

---

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA MANUFACTURING NIGERIA LIMITED

10, Western Industrial Avenue, Isheri  
Riverview Estate  
Lagos - Ibadan Expressway, Ogun State  
NIGERIA  
Web: [nga.sika.com](http://nga.sika.com)

### PRODUCT DATA SHEET

Sikament® RB 846  
May 2024, Version 01.01  
02130200000002184

SikamentRB846-en-NG-(05-2024)-1-1.pdf