

PRODUCT DATA SHEET

Sika AnchorFix®-2+

ANCHORING ADHESIVE FOR MEDIUM TO HIGH LOADS

DESCRIPTION

Solvent and styrene free, epoxy acrylate based, 2-component anchoring adhesive for normal/moderate climate conditions.

USES

Sika AnchorFix®-2+ may only be used by experienced professionals.

As a fast curing anchoring adhesive for all grades of:

- Rebars / reinforcing steel
- Threaded rods
- Bolts and special fastening systems
- Concrete (in cracked and non-cracked)
- Solid masonry
- Steel
- Hard natural stone*
- Solid rock*
- * These substrates may vary greatly, in particular with regard to strength, composition and porosity. Therefore, for each application the suitability of Sika Anchor-Fix®-2+ Adhesive must be tested by first applying the Product only to a sample area. Check in particular bond strength, surface staining and discoloration.

CHARACTERISTICS / ADVANTAGES


- Fast curing
- Standard guns can be used
- High load capacity
- ETA to ETAG 001 for anchoring in concrete
- ETA to ETAG 001 for rebar connections
- Suitable for cracked concrete
- Drinking Water certified
- LEED Attestation available
- Non-sag, even overhead
- Styrene-free
- Low odour
- Low wastage

APPROVALS / CERTIFICATES

- Bonded injection type anchor according to ETAG 001
 Part 1 and 5 Option 1, ETA-14/0346, Declaration of
 Performance 020205010020000011 5034408 (1138),
 certified by notified product certification body 1020,
 certificate of constancy of performance 1020-CPR090-032534, and provided with the CE marking.
- Post installed rebar connection according to ETAG 001 Part 1 and 5 TR 023, ETA-13/0779, Declaration of Performance 020205010020000011 5034408 (1138), certified by notified product certification body 1020, certificate of constancy of performance 1020-CPD-090-036698, and provided with the CE marking
- Drinking Water Certificate: Water Regulations Advisory Scheme Ltd. (WRAS) Approval Number: 1604543

PRODUCT INFORMATION

Packaging	300 ml standard cartridge	12 cartridges per box	
		pallet: 75 boxes	
	350 ml standard cartridge	12 cartridges per box	
	550 ml standard cartridge	pallet: 50 boxes 12 cartridges per box	
	330 mi standard cartriage	pallet: 50 boxes	
	850 ml standard cartridge	8 cartridges per box	
		pallet: 50 boxes	
Colour	Component A: white Component B: black Component A+B mixed: grey		
Shelf life	15 months from date of production All Sika AnchorFix®-2+ cartridges have the expiry date printed on the label.		
Storage conditions	Stored properly in original, unopened, sealed and undamaged packaging in dry conditions at temperatures between +5 $^{\circ}$ C and +25 $^{\circ}$ C. Protect from direct sunlight.		
Density	~1.62–1.70 kg/l (component A) ~1.44–1.50 kg/l (component B) ~1.60–1.68 kg/l (component A+B mixed)		
TECHNICAL INFORMATION			
Compressive Strength	~70 N/mm² (7 days, +20 °C)	(ASTM D 695)	
Modulus of Elasticity in Compression	~7 000 N/mm² (7 days, +20 °C)	(ASTM D 695)	
Tensile Strength in Flexure	~29 N/mm² (7 days, +20 °C)	(ASTM D 790)	
Tensile Strength	~15 N/mm² (7 days, +20 °C)	(ASTM D 638)	
Modulus of Elasticity in Tension	~3 800 N/mm ² (7 days, +20 °C)	(ASTM D 638)	
Service Temperature	Long term (1–2 hours) -40 ° Short term (1–2 hours) +80 °	C min. / +50 °C max (ETAG 001, part 5)	
SYSTEMS			
System Structure	For design details, please refer to the separate documentation provided: Technical Documentation Sika AnchorFix®-2+ 870 43 06		
APPLICATION INFORMATIO	N		
Mixing Ratio	Component A : component B = 10 : 1 by volume		
Layer Thickness	~5 mm max.	~5 mm max.	
Sag Flow	Non-sag, even overhead		
Product Temperature	Sika AnchorFix®-2+ must be at a temperature of between +5 °C and +30 °C for application.		
Ambient Air Temperature	+5 °C min. / +30 °C max.		
Dew Point	Beware of condensation. Substrate temperature during application must be at least 3 °C above dew point.		
Substrate Temperature	+5 °C min. / +30 °C max.		
	•		





Temperature	Open time - Tgel	Curing time - Tcur
+25 °C - +30 °C	4 minutes	40 minutes
+20 °C – +25 °C	5 minutes	50 minutes
+15 °C – +20 °C	6 minutes	75 minutes
+10 °C - +15 °C	8 minutes	85 minutes
+5 °C - +10 °C*	10 minutes	145 minutes

^{*}Minimum cartridge temperature = +5 °C

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY


Mortar and concrete must be older than 28 days. Substrate strength (concrete, masonry, natural stone) must be verified. Pull-out tests must be carried out if the substrate strength is unknown. The anchor hole must always be clean, dry, free from oil and grease etc. Loose particles must be removed from the holes. Threaded rods and rebars have to be cleaned thoroughly from any oil, grease or any other substances and particles such as dirt etc.

MIXING

Getting the cartridge ready: 300 / 550 / 850 ml




1. Unscrew the cap



2. Cut the film




3. Screw on the static mixer




4. Place the cartridge into the gun and start application


Getting the cartridge ready: 350 ml




1.Unscrew the cap



2. remove the cap



3. screw on the static mixer



4. Place the cartridge into the gun and start application






APPLICATION METHOD / TOOLS

Anchors in solid masonry/concrete:




Drilling of hole with an electric drill to the diameter and depth required. Drill hole diameter must be in accordance with anchor size.




The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x)

Important: use oil-free compressors.




The drill hole must be thoroughly cleaned with the special steel brush (brush at least 2x). The diameter of the brush must be larger than the diameter of the drill hole.




The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x)

Important: use oil-free compressors.




The drill hole must be thoroughly cleaned with the special steel brush (brush at least 2x). The diameter of the brush must be larger than the diameter of the drill hole




The drill hole must be cleaned with a blow pump or by compressed air, starting from the bottom of the hole. (at least 2x)


Important: use oil-free compressors.



Pump approx. twice until both parts come out uniformly. Do not use this material. Release the gun pressure and clean the cartridge opening with a cloth.




Inject the adhesive into the hole, starting from the bottom, while slowly drawing back the static mixer.In any case avoid entrapping air. For deep holes extension tubing can be used.



Insert the anchor with a rotary motion into the filled drill hole. Some adhesive must come out of the hole.

Important: the anchor must be placed within the open time.



During the resin hardening time the anchor must not be moved or loaded. Wash tools immediately with Sika® Colma Cleaner. Wash hands and skin thoroughly with warm soap water.

FURTHER INFORMATION

For design details, please refer to the separate documentation provided:

Technical Documentation Sika AnchorFix®-2+ 870 43

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

PRODUCT DATA SHEET Sika AnchorFix®-2+



LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Manufacturing Nigeria LTD 10, Western Industrial Avenue, Isheri Riverview Estate, Lagos-Ibadan Expressway, Nigeria. Tel.:+234 80 90 44 22 21 nga.sika.com







PRODUCT DATA SHEET Sika AnchorFix®-2+ May 2020, Version 01.0 020205010020000011

