

PRODUCT DATA SHEET

Sikafloor®-20 PurCem®

HEAVY DUTY, POLYURETHANE-HYBRID FLOORING SCREED AND COATING



DESCRIPTION

Sikafloor®-20 PurCem® (AE) is a multi-component, water-based coloured polyurethane hybrid flooring screed. It has flat, high abrasion, chemical, impact and slip resistant surface. It is typically installed at 6 - 9 mm.

Suitable for use in hot and tropical climatic conditions.

USES

Sikafloor®-20 PurCem® (AE) may only be used by experienced professionals.

Sikafloor®-20 PurCem® (AE) is used as a final flooring wear layer in Sikafloor® PurCem® HM-20 system build up in areas of high mechanical abrasion and impacts, aggressive chemical attack, thermal shocks and high temperature stresses. The product can also be used as an underlayment and level screed for Sikafloor® PurCem® flooring systems by adding defined aggregates.

CHARACTERISTICS / ADVANTAGES

- Very good chemical resistance
- Excellent mechanical resistance
- High glass transition point
- Non tainting / odourless
- VOC free
- Can be applied to substrates with high moisture content (7 days old or mature damp concrete)

SUSTAINABILITY

LEED Rating

- Complies with AgBB for use in indoor environment.
- Sikafloor®-20 PurCem® (AE) is certified according "Low Emitting Materials as per Al Sa'fat - Dubai Green Building Evaluation System" by Dubai Central Laboratory (DCL) certificate No. CL17020432

APPROVALS / CERTIFICATES

- EN 1186, EN 13130, and prCEN/TS 14234 standards, and the Decree on Consumer Goods, representing the conversion of directives 89/109/EEC, 90/128/EEC and 2002/72/EC for contact with food stuffs, according to test report by ISEGA, 32758 U11 and 32759 U11, both dated December 6th, 2011. (Tests performed on Sikafloor® -20/21/22/29 and 31 PurCem® in standard and LP versions).
- Campden and Chorleywood Food Research Association, reference S/REP/125424/1a and 2a, dated 8th February, 2012.
- Fire classification report according to EN 13501-1 from Exova Warrington Fire for Sikafloor®-20 PurCem® No. 317045, dated 24th of March, 2012.
- Liquid water transmission rate test report from the Technology Centre, reference 15456 dated January 25th, 2012.
- Abrasion resistance tests performed by Face Consultants Ltd., according to BS 8204-2:2003, report reference FC/12/3850, dated January 17th, 2012. (Tests performed on Sikafloor® -20/21 PurCem®).
- Thermal expansion coefficient and freeze-thaw cycle resistance performed at RWTH / IBAC, report no M-1614 dated May 29th, 2012.

PRODUCT INFORMATION

Composition	Water-based polyurethane cement hybrid	
Packaging	Part A	5.0 kg plastic jerrycan
	Part B	4.6 kg plastic jerrycan
	Part C	2 x 19.40 kg plastic lined, double paper bags
	Part D	1.6 kg plastic pouch
	Part A + B + C + D: 50 kg ready to mix units	
Appearance / Colour	Part A	White liquid
	Part B	Brown liquid
	Part C	Natural white powder
	Part D	Colourpack as per list below
	Standard colours: Stone grey, Beige, Grass Green, Oxide Red. Other colours upon request: Traffic Grey, Maize Yellow, Slate Grey.	
Shelf life	Part A	12 months from date of production. Protect from freezing.
	Part B	12 months from date of production. Protect from freezing.
	Part C	6 months from date of production. Must be protected from humidity.
	Part D	12 months from date of production. Protect from freezing.
	Storage conditions	The package must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5 °C and +30 °C.
Density	Part A + B + C + D mixed: ~2.08 kg/l (+20°C)	

TECHNICAL INFORMATION

Shore D Hardness	~80 - 85	(ASTM D 2240)
Compressive Strength	≥ 40 N/mm ² (28 d / +23 °C / 50 % r.h.)	(BS EN 13892-2)
Tensile Strength in Flexure	≥ 10 N/mm ² (28 d / +23 °C / 50 % r.h.)	(BS EN 13892-2)
Tensile Adhesion Strength	Concrete failure	(EN 1542)

SYSTEMS

Systems	Please refer to the System Data Sheet of: Sikafloor® PurCem® HM-20	
		Heavy-duty, lightly textured, high chemical, mechanical and temperature resistant PUCEM hybrid screed

APPLICATION INFORMATION

Mixing Ratio	Mix full units only.
Ambient Air Temperature	+10 °C min. / +30 °C max.
Consumption	~2.08 kg/m ² /mm Consumptions are theoretical and do not include any wastage, additional material need due to porosity, substrate profile etc.
Layer Thickness	Wear coat 6 - 9 mm Underlayment screed 12 - 30 mm (when defined aggregates added)
Relative Air Humidity	85 % max.

Dew Point	Beware of condensation! The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or blooming on the floor finish.		
Substrate Temperature	+10 °C min. / +30 °C max.		
Substrate Moisture Content	Can be installed on substrates with higher moisture content. No ponding water. Check rising moisture. The substrate needs to be visibly dry and have adequate pull-off strength min 1.5 N/mm ² .		
Pot Life	Temperature	Time	
	+10 °C	~35 - 40 min	
	+20 °C	~22 - 25 min	
	+30 °C	~15 - 18 min	
	+35 °C	~12 - 15 min	
Curing Time	Before overcoating Sikafloor® -20 PurCem® allow:		
	Substrate temperature	Minimum	Maximum
	+10 °C	24 h	72 h
	+20 °C	24 h	48 h
	+30 °C	12 h	24 h
+40 °C	12 h	24 h	
Times are approximate and will be affected by changing ambient and substrate conditions, particularly temperature and relative humidity. If used other primers than Scratch Coat refer the Technical Data Sheet of the respective product. Make sure that the primer and the scratch coat layer is fully cured before application of Sikafloor® PurCem® previous layer.			

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

The surface must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc. All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by vacuum. Pull of strength shall not be less than 1.5 N/mm². If in doubt apply a test area first.

MIXING

Homogenise Part A with a low speed electric stirrer and then add Part B and premix Part A and B separately for 30 seconds. Make sure all pigment is uniformly distributed.

For the colourpack version, homogenise Part A neutral with a low speed electric stirrer and add Part D to it. Mix until a uniform colour is achieved. Add Part B and mix A neutral, D and B separately for 30 seconds. Make sure all pigment is uniformly distributed. Start the pan mixer and gradually add Part C (aggregate) to the mixed resin parts over a period of 15 seconds. Allow Part C to blend for further 2 minutes minimum, to ensure complete mixing and a uniform mix is obtained. During the operations, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once (Parts A + B + C or A neutral + B + C + D) to ensure complete mixing. Mix full units only.

Mixing Tools

Refer to the Sikafloor® - PurCem® method statement

APPLICATION

Prior to application, confirm substrate moisture content, relative humidity and dew point. Sikafloor®-20 PurCem® (AE) can be applied using a flat, round edge steel trowel. A short pile roller can be used once or twice, and always in the same direction, to provide a more homogeneous finish to the surface. For further details please refer to the related system data sheet and method statement.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with Thinner C immediately after use. Hardened / cured material can only be mechanically removed.

FURTHER INFORMATION

Please refer to:

- Sikafloor® PurCem® Method Statement
- Sika® Method Statement Mixing and Application of Flooring Systems
- Sika® Method Statement Surface Evaluation & Preparation
- Sikafloor® PurCem® System Data Sheets

IMPORTANT CONSIDERATIONS

- Do not apply to PCC (polymer modified cement mortars) that may expand due to moisture when sealed with an impervious resin.
- Always ensure good ventilation when using Sikafloor®-20 PurCem® (AE) in a confined space, to prevent excessive ambient humidity.
- Freshly applied Sikafloor®-20 PurCem® (AE), must be protected from damp, condensation and direct water contact (rain) for at least 24 hours.
- The material must be conditioned by being stored in an area with an ambient temperature between +15°C and +25°C for a minimum of 48 hours before using.
- Protect the substrate during application from condensation from pipes or any overhead leaks.
- Do not apply to cracked or unsound substrates.
- Always allow a minimum of 48 hours after product application prior to placing into service in proximity with food stuffs.
- Products of the Sikafloor® -PurCem® product range are subject to discolouration when exposed to UV radiation. Extend depends on colour. There are no measurable losses of any properties when this occurs and it is a purely aesthetic matter. Products can be used outside provided the change in appearance is acceptable by the customer.
- In some slow curing conditions, soiling of the surface may occur when opened to foot traffic, even though mechanical properties have been achieved. It is advised to remove dirt using a dry mop or cloth. Avoid scrubbing with water for the first three days.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Manufacturing Nigeria LTD

10, Western Industrial Avenue,
Isheri Riverview Estate,
Lagos-Ibadan Expressway,
Nigeria.

Tel.: +234 80 90 44 22 21
nga.sika.com



ISO 9001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd,
Sika Qatar LLC
ISO 14001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd
OHSAS: Sika UAE LLC,
Sika Gulf B.S.C. (c)

All products are supplied
under a management
system certified to conform
to the requirements of the
quality, environmental and
occupational health &
safety standards ISO 9001,
ISO 14001 and OHSAS
18001.

Product Data Sheet
Sikafloor®-20 PurCem®
May 2020, Version 01.0
020814020020000034

BUILDING TRUST

