

BUILDING TRUST

PRODUCT DATA SHEET

SikaGrind[®]-180 MY NG

Strength enhancing grinding aid for the production of cement

DESCRIPTION

SikaGrind[®]-180 MY is a liquid cement grinding aid with performance enhancing properties designed to increase

the output of cement grinding plants and obtain improved strength development for cements.

USES

- Improve the production rate of the cement grinding system
- Increase the early strength of the cement

FEATURES

SikaGrind[®]-180 MY is a dispersant with the following characteristics:

Neutralisation of electrical charges on the surface of the cement particles

Separation of the cement particles

SikaGrind[®]-180 MY provides the following advantages in the cement production:

Enhanced grinding properties of the cement mill due to less accumulation of material on grinding balls and mill-liners

Higher separator efficiency due to improved cement particle dispersion

Reduced relative power consumption per ton of cement

due to increased output of the grinding system (tons per hour)

•

Easier achievement of the desired cement and improved

powder flow characteristics.

SikaGrind[®]-180 MY gives the following advantages to the finished cement:

PRODUCT DATA SHEET SikaGrind®-180 MY NG November 2024, Version 01.03 021407011000000423 Reduced quantity of "over-milled" particles in the cement

granulometry and easier discharge of the silos

Increased early strengths and economic cement design with clinker replacements

PRODUCT

PRODUCT INFORMATION

Composition	Blend of some special organics
Packaging	• 1 000 kg IBC
Shelf life	12 months from date of production
Storage conditions	Store in undamaged, unopened and sealed original containers at temper- atures between +5 °C and +35 °C. Protect from frost, direct sunlight and contamination. Note: When delivered in bulk, the tanks and equipment used must be free from contaminants.
Appearance and colour	Brown liquid
Density	1.17 +/- 0.02
pH-Value	10.7 +/- 1
Recommended dosage	Typical dosage rates of SikaGrind®-180 MY is between 0.5–2.0 kg per tonne of cement (0.05–0.20 % of total weight = cement clinker + addi- tions). Prior plant trials are necessary to determine optimum dossage because of variables such as clincker properties, cement type, and others.
Dispensing	SikaGrind®-180 MY is added onto the clinker feed shortly before the mill entrance or directly into the grinding mill (first or second compartment). Suitable dosage pumps with adjustable flow rates shall be used for accurate dosing. Note: Periodically, the end of the additive tube/hose shall be checked to ensure that it is not blocked!
Compatibility	Cements treated with SikaGrind®-180 MY are compatible in concretes pro- duced with all commercial admixtures including air entrainers, water reducers, retarders and superplasticizers. The performance of concrete admixtures is not adversely affected by the use of SikaGrind®-180 MY.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which

BUILDING TRUST

PRODUCT DATA SHEET SikaGrind®-180 MY NG November 2024, Version 01.03 021407011000000423



will be supplied on request.

SIKA MANUFACTURING NIGERIA LIMITED

10,Western Industrial Avenue, Isheri Riverview Estate Lagos - Ibadan Expressway, Ogun State NIGERIA Web: nga.sika.com

PRODUCT DATA SHEET SikaGrind®-180 MY NG November 2024, Version 01.03 021407011000000423 SikaGrind-180MYNG-en-NG-(11-2024)-1-3.pdf



BUILDING TRUST