

SIKA[®] BITUME FONDATION

Description

SIKA BITUME FONDATION is a black petroleum solution.

General characteristics

Forms a continuous and homogeneous film that patches the orifices of concrete capillary channels.

Good covering power.

Applicable on a troweled dressing or on concrete.

Applications

Waterproofing of foundations and underground structures in construction and civil engineering.

Ph and Ch (and mechanical) characteristics

Density: about 0,9.

Packaging

30-l drum.

Storage and shelf-life

SIKA BITUME FONDATION stored in a dry and cool place in an unopened packaging has a one-year shelf-life.

Consumption

0,150 to 0,200 litre/m² per layer depending on the substrate roughness.

Instructions

Concretes and mortars must be at least 7 days old.

SIKA BITUME FONDATION is applied using a brush, a roller or a spray gun in two or three layers depending on the substrate absorbency.

Waiting time between two layers

10 hours at 20°C.

Important considerations

SIKA BITUME FONDATION is a flammable product.
Consult data sheet on Minitel 3613, code SIKASECUR

This english version is a translation of the reference french data sheet

Product for strictly professional use only.
«The product described in this data sheet is covered under the manufacturer's product liability policy».



Sika Manufacturing Nigeria LTD
10, Western Industrial Avenue,
Isheri Riverview Estate,
Lagos-Ibadan Expressway,
Nigeria.
Tel. :+234 80 90 44 22 21
nga.sika.com

«The information, and, in particular, the recommendations relating to the application and end-use of SIKA products, are given in good faith based on SIKA's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability

arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the french version of the Technical Data Sheet for the product concerned, copies of which will be supplied on request».